


PELLET LAB ANALYSIS RESULTS “Sparrow”

			Sparrow	Class A1	Class A2
	Standard	Unit			
bulk density (ar)	ISO 17828	[kg/m ³]	640	750>BD>600	750>BD>600
moisture content	ISO 18134-2	[%]	6,7	< 10	<10
ash content 550°C (db)	ISO 18122	[%]	1,15	<0,7	<1,2
net calorific value (ar)	ISO 18125	[MJ/kg]	16,9	> 16,5	>16,5
net calorific value (ar)	ISO 18125	[kWh/kg]	4,7	>4,6	>4,6
diameter	ISO 17829	[mm]	6	6 or 8 ± 1	6 or 8 ± 1